

New World

Textile Testing Laboratory

206 Globe Mills Avenue, Fall River, MA 02724

Tel: (508) 689-1653 Fax: (508) 689-1792

Email: LLeite@Nworld.US

Product: 70 Denier Nylon Multicam FR Coat

Weight,	3.40	Mullens	165	Sprays, %	90
oz./sq.yd.	3.43	ASTM D 751	160	AATCC 22	
ASTM D 3776	3.40		165		
	3.40		170		
	<u>3.46</u>		<u>160</u>		
Average	3.42	Average	164		

F.R. Testing: CPAI-84

Individual 4 seconds Max. Average 2 seconds Max.		Individual 4 seconds Max. Average 2 seconds Max.		Individual 10.0" Max. Average 8.5" Max.	
After Flame		After Glow		Char Length	
Warp	Fill	Warp	Fill	Warp	Fill
0	0	0	0	3.7	2.9
0	0	0	0	3.8	3.9
0	0	0	0	4.6	3.5
0	0	0	0	4.4	3.1
<u>0</u>	<u>0</u>	<u>0</u>	<u>0</u>	<u>4.1</u>	<u>3.7</u>
0	0	0	0	4.1	3.4

5 Readings w/Average

Colorfastness To:

Laundering, 2A wash

AATCC-61

Shade Change: 4.5

Staining: 4.5