



Textile Testing Laboratory

206 Globe Mills Avenue, Fall River, MA 02724

Tel: (508) 689-1653 Fax: (508) 689-1792

Email: LLeite@Nworld.US

Product: 70 Denier - Multicam Nylon FR Finish

Test: Fed. Std. 191A
Unless Noted Otherwise

Roll #1

Page 1 of 2

WIDTH
ASTM D 3374

61 1/2
60 1/2

TENSILE, lbs.
ASTM D 5034

Warp
129
138
136
138
135
135

5 Readings w/average

Fill
118
125
119
128
125
120
131
124
124

8 Readings w/average

Test: Fed. Std. 191A
Unless Noted Otherwise

Roll #1

TEARS, lbs.

ASTM D 1424

Warp

6.5

5.2

5.8

5.9

6.2

5 Readings w/average

5.9

Fill

7.2

7.3

7.1

6.8

6.5

5 Readings w/average

7.0

SEAM SLIPPAGE

ASTM D 434

Warp

52

48

50

49

53

5 Readings w/average

50

Fill

46

49

49

47

48

5 Readings w/average

48